


Amendments to the Specification:

Please amend Paragraph 0048 as follows:

[0001] Preferably, the adhesive polymer formulation comprises a polyacrylate adhesive polymer of the general formula (I):



wherein x represents the number of repeating units sufficient to provide the desired properties in the adhesive polymer and R is H or a lower (C₁ - C₁₀) alkyl, such as ethyl, butyl, 2-ethylhexyl, octyl, decyl and the like. More specifically, it is preferred that the adhesive polymer matrix comprises a polyacrylate adhesive copolymer having a 2-ethylhexyl acrylate monomer and approximately 50-60% w/w of vinyl acetate as a co-monomer. An example of a suitable polyacrylate adhesive copolymer for use in the present invention includes, but is not limited to, that sold under the tradename of DURO TAK ~~Duro-Tak~~ 87-4098 by National Starch and Chemical Co., Bridgewater, N.J., which comprises a certain percentage of vinyl acetate co-monomer.

Please amend Paragraph 0081 as follows:

[0002] Materials:	<u>mg</u>	<u>wt%</u>
Humectant PVP/VA-S630:	9.66	1.25
Skin permeation enhancers:		
DMSO	73.77	9.51
Lauryl lactate (Ceraphyl® 31)	24.59	3.10

Ethyl lactate	24.59	3.10
Capric Acid	18.54	2.39
Adhesive polymer: <u>DURO TAK</u> Duro-Tak 87-4098	617.59	79.65
Hormones:		
Levonorgestrel	4.48	0.58
Ethinyl estradiol	2.20	0.28
Backing layer - Scotchpak® 9732 (3M Company)	16 sheets	-----
Release liner - Scotchpak® 1022 (3M Company)	<u>16 sheets</u>	<u>-----</u>
TOTAL	775.41 mg	100.00%

Please amend Paragraph 0082 as follows:

[0003] Hormones were dissolved and dispersed in a solution comprising PVP/vinyl acetate and the combination of skin permeation enhancers. DURO TAK ~~Duro-Tak~~ 87-4098 (33% solid content) adhesive polymer solution was added, and the container was sealed. The solution was stirred using a magnetic stirring bar at approximately 200 rpm at room temperature for 3 hours, to form a homogeneous solution. The stirred solution was deaerated by allowing it to stand without stirring for one hour or until all air bubbles had disappeared. The deaerated solution was coated onto a piece of the backing layer to a thickness of 700 µm, then dried at 60°C for 15 minutes, using a laboratory coating/drying machine (Model LTSV/LTH, Werner Mathis, Switzerland). The dried adhesive polymer matrix was laminated with a piece of release liner of the same size as the backing layer, to form a sheet of THDS. The sheets were cut into dosage units of 15 cm² using a steel rule die and hydraulic press at 4000 psi. Each dosage unit was individually packaged in a paper or foil pouch and stored at 4°C.

Please amend Paragraph 0085 as follows:

[0004] Average thickness of adhesive polymer matrix: 100 µm
Average composition of adhesive polymer matrix:
Component: mg per 15 cm² patch wt%

DOCKET NO.: 48378-0003-00-US
Application No.: 10/621,711
Office Action dated: August 4, 2006

PATENT

PVP/VA-S630:	10.0	3.34
<u>DURO TAK</u> Duro-Tak 87-4098:	211.3	70.43
Enhancers:		
DMSO:	24.0	8.00
Lauryl lactate:	25.2	8.40
Ethyl lactate:	4.5	1.50
Capric Acid:	18.0	6.00
Hormones:		
Levonorgestrel	4.7	1.57
Ethinyl estradiol	<u>2.3</u>	<u>0.77</u>
TOTAL:	300.0	100.00